

536, 943

## (12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



27 MAY 2005



(43) International Publication Date  
10 June 2004 (10.06.2004)

PCT

(10) International Publication Number  
**WO 2004/047571 A2**

- (51) International Patent Classification<sup>7</sup>: **A24D 3/06**
- (21) International Application Number:  
PCT/GB2003/005151
- (22) International Filing Date:  
26 November 2003 (26.11.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
0227662.4 27 November 2002 (27.11.2002) GB
- (71) Applicant (for all designated States except US): **FILTRONA INTERNATIONAL LIMITED** [GB/GB]; 110 Park Street, London W1Y 3RB (GB).
- (72) Inventor; and
- (75) Inventor/Applicant (for US only): **MCCORMACK, Anthony, Denis** [GB/GB]; Dalry, Elm Bank Road, Wylam, Northumberland NE41 8HS (GB).
- (74) Agent: **GEERING, Keith, Edwin**; Reddie & Grose, 16 Theobalds Road, London WC1X 8PL (GB).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (*regional*): ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**  
— without international search report and to be republished upon receipt of that report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: TOBACCO SMOKE FILTER

(57) **Abstract:** A tobacco smoke filter which gives acceptable vapour phase filtration and flavour delivery in the presence of volatile flavourant (e.g. menthol), the filter containing activated carbon in which (1) pores of under 2 nm pore diameter (micropores) provide a pore volume of at most 0.3 cm<sup>3</sup>/g (NZ); and (2) (a) pores of 2 to 50 nm pore diameter (mesopores) provide a pore volume of at least 0.25 cm<sup>3</sup>/g (N<sub>2</sub>) and/or (b) pores of 7 to 50 nm diameter (larger mesopores) provide a pore volume of at least 0.12 cm<sup>3</sup>/g (Hg).

WO 2004/047571 A2

TOBACCO SMOKE FILTER

This invention relates to tobacco smoke filters containing particulate sorbent.

Such use of sorbent particles to remove vapour phase  
5 (VP) components from tobacco smoke is well known. Cigarettes containing volatile flavourant (e.g. menthol) are also well known. However, prior attempts to use both volatile flavourant and particulate sorbent in a filter cigarette have been unsuccessful, it having proved  
10 impossible to provide a satisfactory level of flavour delivery whilst maintaining a satisfactory level of VP constituent removal by the particulate sorbent.

We have found that this problem can be overcome by a tobacco smoke filter containing activated carbon in which  
15 (1) pores of under 2 nm pore diameter (micropores) provide a pore volume of at most 0.3 cm<sup>3</sup>/g (N<sub>2</sub>); and (2) (a) pores of 2 to 50 nm pore diameter (mesopores) provide a pore volume of at least 0.25 cm<sup>3</sup>/g (N<sub>2</sub>) and/or (b) pores of 7 to 50 nm diameter (larger mesopores) provide a pore volume of  
20 at least 0.12 cm<sup>3</sup>/g (Hg). An activated carbon without micropore volume has poor VP removal performance which is reduced yet further or nullified in the presence of volatile flavourant, and the indicated micro/meso pore

- 2 -

combinations are necessary to permit the required balance of flavour delivery and VP removal. Herein a pore volume expressed in  $\text{cm}^3/\text{g}$  ( $\text{N}_2$ ) means said volume as measured by nitrogen porosimetry, using a Micromeritics Tristar 3000  
5 for measurement of the nitrogen adsorption/desorption isotherms and characterising the pore size distribution via the BJH method on the desorption branch of the isotherm. A pore volume or surface area expressed in  $\text{cm}^3/\text{g}$  (Hg) or  $\text{m}^2/\text{g}$  (Hg) means said value as measured by  
10 mercury porosimetry using a contact angle of  $140^\circ$  and a surface tension value of 480 dynes/cm.

Accordingly the present invention provides a tobacco smoke filter containing activated carbon which carbon has a micropore volume provided by micropores of under 2 nm  
15 pore diameter, said micropore volume being up to  $0.3 \text{ cm}^3/\text{g}$  ( $\text{N}_2$ ), and in which carbon mesopores of 2 to 50 nm pore diameter provide a mesopore volume of at least  $0.25 \text{ cm}^3/\text{g}$  ( $\text{N}_2$ ); such a filter wherein at least  $0.12 \text{ cm}^3/\text{g}$  (Hg) of said mesopore volume is provided by mesopores of 7 to 50  
20 nm pore diameter; and a tobacco smoke filter containing activated carbon which carbon has a micropore volume provided by micropores of under 2 nm pore diameter, said micropore volume being up to  $0.3 \text{ cm}^3/\text{g}$  ( $\text{N}_2$ ), and in which carbon mesopores of 7 to 50 nm pore diameter provide a  
25 mesopore volume of at least  $0.12 \text{ cm}^3/\text{g}$  (Hg).

- 3 -

In the activated carbon used according to the invention pores of over 50 nm pore diameter (macropores) preferably provide a pore surface area of at least 5 m<sup>2</sup>/g (Hg), most preferably of 6 or more m<sup>2</sup>/g (Hg).

5           The designation of pores of less than 2 nm, 2 to 50 nm, and over 50 nm size (diameter) as micro-, meso- and macro-pores is in accord with accepted IUPAC terminology and definition.

          The micropore volume provided by said micropores is  
10       preferably at most 0.26 cm<sup>3</sup>/g (N<sub>2</sub>), more preferably 0.15 cm<sup>3</sup>/g (N<sub>2</sub>) or less. The mesopore volume provided by said 2 to 50 nm mesopores may for example be about 0.3 cm<sup>3</sup>/g (N<sub>2</sub>) and is preferably over 0.4 or over 0.5 cm<sup>3</sup>/g (N<sub>2</sub>); the preferred range is thus from 0.3 to 0.5 or higher cm<sup>3</sup>/g  
15       (N<sub>2</sub>). The mesopore volume provided by the 7 to 50 nm larger mesopores is preferably 0.13 cm<sup>3</sup>/g (Hg) or higher, and can be over 0.3 or over 0.5 cm<sup>3</sup>/g (Hg); the preferred range is thus from 0.13 to 0.5 or higher cm<sup>3</sup>/g (Hg).

          We have most unexpectedly found that activated carbon  
20       of such carefully controlled micro/meso porosity - and preferably micro/meso/macro porosity - (a) shows a satisfactory level of adsorption of volatile flavourant such as menthol (not too little and not too much); (b) releases sufficient of the flavourant under smoking

- 4 -

conditions to deliver satisfactory taste; (c) shows good adsorption of VP components from tobacco smoke; and (d) retains a satisfactory (albeit reduced) level of this VP removal even in the presence of volatile flavourant such as menthol. This combination of properties has not heretofore been attainable.

Accordingly the invention also provides a tobacco smoke filter according to the invention incorporated in a filter cigarette containing volatile flavourant - e.g. menthol. Such a filter cigarette provides for the first time the combination of flavour delivery to give an acceptably flavoured taste with an acceptable reduction in delivery of VP smoke components.

The filter according to the invention may be of any design previously proposed for particulate sorbent-containing tobacco smoke filters. For example the carbon may be dispersed throughout a filter plug, carried on the tow or fibres or sheet material which is gathered to form the plug; it may instead be adhered to one or more threads which extend through the matrix of the filter plug or be adhered to the inner face of a wrapper around the filter plug; or it may form a bed sandwiched between a pair of plugs (e.g. of cellulose acetate tow) in a common wrapper. The carbon may be treated with the flavourant prior to filter production so that it acts as a carrier for the

- 5 -

flavourant and minimises migration of the flavourant during storage. Instead, the carbon could be used in a suitable filter in the unflavoured state, with the flavourant being added to another part of the filter and/or to the cigarette with which the filter is used and/or to the filter cigarette packaging. The flavourant might be carried on a wrapper around a filter plug or on one or more threads through a filter plug, and such plug may be the plug which also carries the activated carbon or a separate plug.

Filters according to the invention may additionally include one or more particulate sorbents other than the activated carbon required by the invention (e.g. silica gel, or a different carbon), mixed with the carbon required by the invention and/or separate from this.

The invention is illustrated by the following Examples, in which Examples B, C, D and H are according to the invention and the remainder are comparisons.

#### EXAMPLES

For each Example a sample of the respective activated carbon was dried and exposed to a menthol atmosphere in a desiccator at 55°C for 4 days, and the increase in weight was recorded. 'Triple granular' cigarette filters were then assembled, each containing 100 mg of the mentholated

- 6 -

carbon in a packed bed between two cellulose acetate filter segments. The filter cigarettes were smoked under ISO conditions (35 cm<sup>3</sup> puffs, each of two seconds duration, taken once per minute) and the menthol yields from the cigarettes were measured. The vapour phase of cigarette smoke was also collected and the percentage reduction of a selected number of vapour phase compounds measured; the mean reduction in these VP compounds, and the reduction obtained from an equivalent filter with 100 mg of the same carbon prior to exposure to menthol, were measured relative to an equivalent filter cigarette with no carbon.

The results are summarised in the following Table which gives the porosity parameters for the various carbons employed and the measured performances of the filters using them. Examples B, C, D and H used activated carbons according to the requirements of the invention, whilst the remainder did not. Comparison Example A used a standard coconut-based carbon as typically used in prior cigarette filters, whilst Comparison Examples E to G and I to M used other carbons whose micro/meso/macro porosity led to poor results. Comparison Example K showed good menthol uptake and yield, but with immeasurably low carbon micropore volume its VP removal performance was low and reduced to substantially zero in the presence of menthol. Comparison Examples I, J, L and M showed active VP removal

- 7 -

after mentholation but gave markedly inadequate menthol yield, whilst the remaining Comparison Examples (A and E to G) were markedly inadequate for both VP removal and menthol yield.



T A B L E

EXAMPLE	A	B	C	D	E	F	G
Micropore Volume - (cm <sup>3</sup> /g) (N <sub>2</sub> )	0.46	0.26	0.11	0.12	0.52	0.33	0.23
2-50 nm Mesopore Volume -cm <sup>3</sup> /g (N <sub>2</sub> )	0.09	0.30	0.44	0.51	0.36	0.25	0.04
7-50nm Mesopore Volume -cm <sup>3</sup> /g (Hg)	0.06	0.13	0.34	0.54	0.21	0.15	na *
Macropore Area -m <sup>2</sup> /g (Hg)	1.9	6.4	6.9	12.2	1.4	4.9	na *
Menthol Uptake %	18.6	27.3	27.5	23	57.1	18.9	11.5
Menthol Yield (mg/cig)	0.03	0.73	0.44	0.72	0.07	0.06	0.15
Mean VP (unmentholated) (%)	53	85	45	61	85	45	47
Mean VP (mentholated) (%)	<5	24	24	36	<5	<5	<5

TABLE (Continued)

EXAMPLE	H	I	J	K	L	M
Micropore Volume - (cm <sup>3</sup> /g) (N <sub>2</sub> )	0.19	0.35	0.43	nm *	0.50	0.31
2-50 nm Mesopore Volume -cm <sup>3</sup> /g (N <sub>2</sub> )	0.29	1.05	0.92	0.49	1.10	0.28
7-50nm Mesopore Volume -cm <sup>3</sup> /g (Hg)	0.13	0.20	0.29	na *	0.21	0.10
Macropore Area -m <sup>2</sup> /g (Hg)	8.0	2.8	1.1	na *	2.5	3.7
Menthol Uptake %	20	34.6	34.9	39.7	39.1	20
Menthol Yield (mg/cig)	0.58	0.08	0.12	0.99	0.04	0.00
Mean VP (unmentholated) (%)	79	87	75	27	91	55
Mean VP (mentholated) (%)	25	46	45	0	30	35

\* na - not ascertained

\* nm - effectively zero - too small to measure

- 10 -

C L A I M S:

1. A tobacco smoke filter containing activated carbon which carbon has a micropore volume provided by micropores of under 2 nm pore diameter, said micropore volume being  
5 at most 0.3 cm<sup>3</sup>/g (N<sub>2</sub>), and in which carbon mesopores of 2 to 50 nm pore diameter provide a mesopore volume of at least 0.25 cm<sup>3</sup>/g (N<sub>2</sub>).
2. A tobacco smoke filter containing activated carbon which carbon has a micropore volume provided by micropores  
10 of under 2 nm pore diameter, said micropore volume being at most 0.3 cm<sup>3</sup>/g (N<sub>2</sub>), and in which carbon mesopores of 7 to 50 nm pore diameter provide a mesopore volume of at least 0.12 cm<sup>3</sup>/g (Hg).
3. A tobacco smoke filter according to claim 1 wherein  
15 at least 0.12 cm<sup>3</sup>/g (Hg) of said mesopore volume is provided by mesopores of 7 to 50 nm pore diameter.

- 11 -

4. A filter according to any preceding claim wherein macropores of over 50 nm diameter provide a surface area of at least 5 m<sup>2</sup>/g (Hg).

5. A filter according to any preceding claim wherein  
5 said micropore volume is at most 0.26 cm<sup>3</sup>/g (N<sub>2</sub>).

6. A filter according to any preceding claim wherein said micropore volume is at most 0.15 cm<sup>3</sup>/g (N<sub>2</sub>).

7. A filter according to any preceding claim wherein said 2 to 50 nm mesopore volume is about 0.3 cm<sup>3</sup>/g (N<sub>2</sub>).

10 8. A filter according to any of claims 1 to 6 wherein said 2 to 50 nm mesopore volume is over 0.4 or over 0.5 cm<sup>3</sup>/g (N<sub>2</sub>).

9. A filter according to any preceding claim wherein said 7 to 50 nm mesopore volume is at least 0.13 cm<sup>3</sup>/g  
15 (Hg).

- 12 -

10. A filter according to any preceding claim wherein  
said 7 to 50 nm mesopore volume is over 0.3 or over 0.5  
cm<sup>3</sup>/g (Hg).

11. A filter cigarette containing volatile flavourant and  
5 including a filter according to any preceding claim.

12. A filter cigarette according to claim 11 wherein said  
flavourant comprises menthol.

13. A filter cigarette according to claim 11 or 12  
wherein said flavourant is applied to said activated  
10 carbon.

14. A filter cigarette according to any of claims 11 to  
13 wherein said flavourant is applied to a part of said  
filter or cigarette other than said activated carbon  
15 and/or to packaging for said cigarette.

(19) World Intellectual Property  
Organization  
International Bureau



27 MAY 2004



(43) International Publication Date  
10 June 2004 (10.06.2004)

PCT

(10) International Publication Number  
**WO 2004/047571 A3**

(51) International Patent Classification<sup>7</sup>: **A24D 3/16**

(21) International Application Number:  
PCT/GB2003/005151

(22) International Filing Date:  
26 November 2003 (26.11.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
0227662.4 27 November 2002 (27.11.2002) GB

(71) Applicant (for all designated States except US): **FIL-TRONA INTERNATIONAL LIMITED** [GB/GB]; 110 Park Street, London W1Y 3RB (GB).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **MCCORMACK, Anthony, Denis** [GB/GB]; Dalry, Elm Bank Road, Wylam, Northumberland NE41 8HS (GB).

(74) Agent: **GEERING, Keith, Edwin**; Reddie & Grose, 16 Theobalds Road, London WC1X 8PL (GB).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(88) Date of publication of the international search report:  
16 September 2004

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: TOBACCO SMOKE FILTER

(57) Abstract: A tobacco smoke filter which gives acceptable vapour phase filtration and flavour delivery in the presence of volatile flavourant (e.g. menthol), the filter containing activated carbon in which (1) pores of under 2 nm pore diameter (micropores) provide a pore volume of at most 0.3 cm<sup>3</sup>/g (NZ); and (2) (a) pores of 2 to 50 nm pore diameter (mesopores) provide a pore volume of at least 0.25 cm<sup>3</sup>/g (N<sub>2</sub>) and/or (b) pores of 7 to 50 nm diameter (larger mesopores) provide a pore volume of at least 0.12 cm<sup>3</sup>/g (Hg).

WO 2004/047571 A3

# INTERNATIONAL SEARCH REPORT

International Application No.

PC/GB 03/05151

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 7 A24D3/16

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
IPC 7 A24D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, COMPENDEX, FSTA, WPI Data, PAJ

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	JP 60 027375 A (JAPAN TOBACCO & SALT PUBLIC; TOYO BOSEKI) 12 February 1985 (1985-02-12) the whole document	1-3
Y	WO 02/37990 A (BEREMAN ROBERT D ; VECTOR TOBACCO BERMUDA LTD (US)) 16 May 2002 (2002-05-16) page 21, line 27 -page 22, line 3; claim 22 --- -/-	1,2

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*G\* document member of the same patent family

Date of the actual completion of the international search

20 July 2004

Date of mailing of the international search report

27/07/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Pille, S

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 03/05151

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,Y	LEE Y-S ET AL: "Preparation and characterization of trilobal activated carbon fibers" CARBON, XX, XX, vol. 41, no. 13, 2003, pages 2573-2584, XP004458786 ISSN: 0008-6223 column 2581; figures 10,12; table 4	1,2
A	US 3 636 957 A (SAFFER CHARLES M JR) 25 January 1972 (1972-01-25) claims 1,2	1,2
A	RU 2 064 281 C (MALAKHOVA MARGARITA YA ;OBOLENSKIJ STANISLAV V (RU)) 27 July 1996 (1996-07-27) abstract	1,2



# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 03/05151

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
JP 60027375	A	12-02-1985	JP 1318777 C	29-05-1986
			JP 60045918 B	12-10-1985
WO 0237990	A	16-05-2002	AU 2890102 A	21-05-2002
			EP 1408780 A2	21-04-2004
			US 2003000538 A1	02-01-2003
			WO 0237990 A2	16-05-2002
US 3636957	A	25-01-1972	NONE	
RU 2064281	C	27-07-1996	RU 2064281 C1	27-07-1996